

# MIT Open Access Articles

## Self-Assembled Nanocoatings Protect Microbial Fertilizers for Climate-Resilient Agriculture

The MIT Faculty has made this article openly available. *Please share* how this access benefits you. Your story matters.

Citation: JACS Au 2023, 3, 11, 2973–2980

As Published: 10.1021/jacsau.3c00426

Publisher: American Chemical Society

Persistent URL: https://hdl.handle.net/1721.1/158304

**Version:** Final published version: final published article, as it appeared in a journal, conference proceedings, or other formally published context

Terms of use: Creative Commons Attribution-NonCommercial-NoDerivatives





Letter

## Self-Assembled Nanocoatings Protect Microbial Fertilizers for Climate-Resilient Agriculture

Benjamin Burke,<sup>†</sup> Gang Fan,<sup>†</sup> Pris Wasuwanich, Evan B. Moore, and Ariel L. Furst\*

**Cite This:** JACS Au 2023, 3, 2973–2980



| ACCESS | III Metrics & More | Article Recommendations | s Supporting Information |
|--------|--------------------|-------------------------|--------------------------|
|--------|--------------------|-------------------------|--------------------------|

**ABSTRACT:** Chemical fertilizers have been crucial for sustaining the current global population by supplementing overused farmland to support consistent food production, but their use is unsustainable. *Pseudomonas chlororaphis* is a nitrogen-fixing bacterium that could be used as a fertilizer replacement, but this microbe is delicate. It is sensitive to stressors, such as freeze-drying and high temperatures. Here, we demonstrate protection of *P. chlororaphis* from freeze-drying, high temperatures (50 °C), and high humidity using self-assembling metal-phenolic network (MPN) coatings. The composition of the MPN is found to significantly impact its protective efficacy, and with optimized compositions, no viability loss is observed for MPN-coated microbes under conditions where uncoated cells do not survive.



Further, we demonstrate that MPN-coated microbes improve germination of seeds by 150% as compared to those treated with fresh *P. chlororaphis*. Taken together, these results demonstrate the protective capabilities of MPNs against environmental stressors and represent a critical step towards enabling the production and storage of delicate microbes under nonideal conditions.

**KEYWORDS:** Regenerative agriculture, temperature-sensitive microbes, self-assembling nanomaterials, metal-phenolic networks, nanoencapsulation

### INTRODUCTION

Chemical fertilizers have been essential to feed the current global population, supplementing overused farmland to support consistent food production. But these chemicals are unsustainable;<sup>1,2</sup> they damage the environment,<sup>3,4</sup> and they contribute to greenhouse gas emissions.<sup>5,6</sup> Further, agricultural runoff containing chemical fertilizers can enter surface and groundwater<sup>7,8</sup> and damage native ecosystems.<sup>9,10</sup> In addition to the environmental concerns, chemical fertilizer is costly, representing between 20% and 36% of a farm's operating budget.<sup>11</sup> In the past two years, chemical fertilizer prices have nearly tripled, climbing from \$94 to \$232 per acre of corn.<sup>12,13</sup> This cost impacts consumer food prices and can lead to decreased yields due to sub-optimal fertilizer application.<sup>1</sup> These environmental and economic impacts necessitate alternative agricultural solutions; land for agriculture is a finite resource, and its long-term sustainable use is essential for food stability.

Microbes offer sustainable alternatives to chemical fertilizers, especially due to their native role in plant growth.<sup>14-16</sup> Microbes can efficiently process essential nutrients (*i.e.*, nitrogen, phosphorus, and sulfur) to render them bioavailable for plants, they can manipulate plant hormone signaling,<sup>17</sup> and they can stop invasive pathogens.<sup>18</sup> Because of their importance, researchers have worked to deliver microbes to

soil, but critical species are difficult to produce and transport because of their sensitivity to temperature<sup>19</sup> and humidity.<sup>20</sup> Accordingly, a platform to stabilize delicate microbes against stressors during processing, storage, and transport would enable widespread agricultural adoption.

We recently reported metal-phenolic network (MPN) coatings that serve as synthetic spore coatings,<sup>21-23</sup> protecting microbes from the drying process and anaerobes from oxygen exposure. MPNs are composed of polyphenols and metal ions that assemble into two-dimensional networks.<sup>24-27</sup> Diverse polyphenols and metal ions have been used to assemble these materials, and the identities of the components have been linked to the physical properties of the final assembled network. Importantly for agricultural applications, the components of these materials are generally recognized as safe (GRAS) by the U.S. Food and Drug Administration (FDA).

Received:July 31, 2023Revised:October 23, 2023Accepted:October 24, 2023Published:October 30, 2023







**Figure 1.** Metal–phenolic network (MPN) assembly on *P. chlororaphis* and its fluorescence images. (a) Cells were coated with a mixture of polyphenols (TA, EGCG, and GA) and metal ions (Fe and Mn). (b) Cells were treated with a live-dead staining kit. Shown are fluorescence images of uncoated and Fe<sup>III</sup>-TA-coated *P. chlororaphis* in the FITC channel (SYTO-9) and TxRed channel (propidium iodide) and as merged images. Scale bars are 20  $\mu$ m. The viabilities of *P. chlororaphis* were 98.3% (uncoated), 98.4% (Fe<sup>III</sup>-TA-coated), and 79.6% (Fe<sup>III</sup>-TA-coated but without MOPS addition).

Here, we establish the ability of these materials to protect the agriculturally-important nitrogen-fixing bacteria Pseudomonas chlororaphis.<sup>28</sup> P. chlororaphis natively interacts with plant roots and fixes nitrogen at them.<sup>29-31</sup> It can also protect plants against phytopathogenic fungi and pests.<sup>32,33</sup> However, P. chlororaphis is highly unstable at elevated temperatures, and prior efforts to protect this species have failed.<sup>34</sup> We demonstrate the protection of P. chlororaphis with MPNs. Importantly, we find that the MPN composition plays a critical role in protective efficacy, based on both the valency of the metal as well as the size and number of chelation sites on the polyphenol. Upon determining the optimal MPN composition for P. chlororaphis protection, the optimal compositions were shown to enable these microbes to survive harsh environmental exposure including lyophilization, storage at temperatures as high as 50 °C and humidity of 48% (relative humidity). We further demonstrate that our formulated P. chlororaphis is more beneficial to seed germination than even fresh microbes. Together, these results establish that MPN composition directly impacts protective behavior.

#### RESULTS AND DISCUSSION

We have shown that MPNs readily form on diverse prokaryotic microbes, including *Bacillus subtilis* and *Bacteroides thetaiotao-micron*.<sup>21-23</sup> *P. chlororaphis* is a nitrogen-fixing species that is natively found in soil ecosystems and has been used as a bioinoculant for agriculture because of its beneficial properties, making it an important target for protection. Additionally, *P.* 

*chlororaphis* is especially useful for studying the MPN protective efficacy because of its well-known temperature instability. In previous work, we have shown that MPNs can significantly improve protection of living biotherapeutics and probiotics to enable their delivery.<sup>21-23</sup> Here, we find that the components of the MPN significantly impact their protective efficacy against freeze-drying, high temperatures, and high humidity.

## MPN Formation on *P. chlororaphis* and Lyophilization Protection

MPNs are higher-dimensional coordination complexes of metal ions and polyphenols that form through self-assembly. Though a diverse array of polyphenols and metal ions can be used for MPN formation, we have focused on three wellstudied polyphenols that are GRAS approved by the FDA (Figure 1a). These three polyphenols, tannic acid (TA), epigallocatechin gallate (EGCG), and gallic acid (GA), span the range of molecular diameters and number of chelation sites, with TA being both the largest with the most catechols and GA being the smallest with the fewest catechol groups. In the presence of a di- or trivalent cation, the polyphenols chelate and generate an extended coordination network. We have generally observed more structurally rigid assemblies with trivalent cations, and we want to focus on metals that are beneficial and have low risk of cytotoxicity.<sup>25,35-37</sup> We therefore focused on Fe<sup>3+</sup>, Mn<sup>3+</sup>, Al<sup>3+</sup> and Zn<sup>2+</sup> as metal components of the MPN. Upon transition of the MPN formation solution to a



**Figure 2.** MPN protection of lyophilized *P. chlororaphis* under extreme temperatures. (a) Overview of workflow for microbial protection with MPNs, followed by exposure to stressors. (b) Photo of 96-well plate containing *P. chlororaphis* coated in MPNs composed of diverse metal ions and polyphenols. The bright colors are indicative of the ligand-to-metal charge transfer band that emerges. (c)  $OD_{600}$  of lyophilized *P. chlororaphis* following 48 h of growth in the presence and absence of tannic-acid-based MPNs. The lyophilized cells were stored at various temperature (20, 25, 30, 35, and 40°C) and 43% relative humidity (RH) for ten days before inoculations. (d) CFU counts from serial dilution plating of MPN-coated lyophilized *P. chlororaphis* after storage under 50°C and 48% RH over five days (The coating thickness was controlled by repeating the coating step multiple times). Error bars represent standard deviations of n = 3 replicates. (e) CFU counts from serial dilution plating of lyophilized *P. chlororaphis* under extreme conditions (top 37°C, bottom 50°C, relative humidity varies) using a mixture of polyphenols (TA, EGCG, and GA) and metal ions (Fe and Mn). (h = hours, d = days, H = 43% RH under 37°C or 48% RH under 50°C, and D = dry condition.) Error bars represent standard deviations of n = 50 replicates.

pH above 8.0, the metal ions chelate the phenolic groups of the polyphenols, forming well-defined coordination centers.

Through UV-vis spectroscopy, we readily established the formation of MPNs on *P. chlororaphis* through the appearance of a well-defined ligand-to-metal charge transfer (LMCT) band upon full deprotonation and coordination of the network. We have previously demonstrated that the appearance of this LMCT band corresponds to the formation of contiguous coreshell coatings on microbial substrates (Figure 2b).<sup>22</sup> In

addition to the UV–vis verification of MPN formation, we imaged cells using a fluorophore-BSA complex that specifically interacts with MPNs (and not uncoated cells, Figures S1, S2). We confirmed through these images that the MPNs form a contiguous coating on the microbes that is not present on the uncoated cells. The consistent fluorescence across the surface of the coated cells confirms that uniform core-shell structures are formed on these microbes, as they have for us in previous reports.<sup>21-23</sup> Moreover, as with other strains we evaluated, the

viability of MPN-coated *P. chlororaphis* (98.4%) is comparable to that of the uncoated controls (98.3%) immediately following coating. This was assessed by live and dead staining with fluorescence microscopy (Figure 1b). We also found that the addition of a MOPS buffer was critical for maintaining the viability of MPN-coated *P. chlororaphis*. In contrast, loosely formed MPNs and low pH were found to negatively affect cell viability.<sup>21-23</sup> Both of these results are critical, as the components of the MPNs on their own are associated with toxicity, which we observe when they are not set by using a high pH buffer. Thus, we demonstrate that setting the MPN coating with a basic MOPS buffer is necessary to observe the MPN protective effects.

Following confirmation of MPN formation on the bacteria and validation of viability maintenance, we evaluated MPN protection against key stressors that P. chlororaphis would encounter during formulation and production. After growth, the first step in processing microbes is to enable their effective transport and delivery via drying. However, such processes cause significant stress and damage to cells, leading to decreases in viability of between three and six orders of magnitude. Thus, we evaluated the impact of the MPNs on protecting P. chlororaphis from the freeze-drying (lyophilization) process. Lyophilization generally requires freezing a sample in liquid nitrogen, followed by sublimation of the ice under vacuum. Both steps cause significant stress to microbes. However, we previously demonstrated that MPNs significantly improve survival following lyophilization, even without additional cryoprotectants, which we also observe here.

For evaluation of stress tolerance, we coated *P. chlororaphis* in either two or four layers of MPNs composed of the aforementioned components. Two and four layers of MPNs were selected because we find these to be the best balance between protection and nonhindered microbial growth. Two layers are the minimum required to observe protection with many strains, and four layers provide additional protection in many cases but do not significantly hinder microbial division. Additional coatings beyond 4 layers significantly inhibit microbial division and often do not offer additional protective benefits.

Following coating and drying the microbes, we evaluated their viability using both optical density for growth analysis at 600 nm (OD<sub>600</sub>) and serial dilution plating for colony-forming unit (CFU) counting. We additionally evaluated *P. chlororaphis* growth following coating, lyophilization, and rehydration using a viability stain. The MPN-coated *P. chlororaphis* reached exponential phase after incubation for 15 h, whereas exponential growth of the uncoated control was delayed to 35 h (Figures S3, S4). This improvement in growth lag indicates that MPN-coated *P. chlororaphis* samples have more viable cells remaining than their uncoated counterparts. Because of the success of MPN protection against these initial stressors for *P. chlororaphis*, we investigated additional critical stressors.

#### Temperature Stability of MPN-Coated P. chlororaphis

A major challenge with *P. chlororaphis*, among many other living microbial agriculture products, is their long-term stability at temperatures above refrigeration. Cold storage and transport are the standard for biologics, but these processes are costly and energy-intensive and require centralized facilities for storage. Additionally, over one billion people globally live farther than 20 km from an all-weather road. This limitation prevents access to large transportation vehicles required for most cold transport, which is currently essential for transport of agricultural products.<sup>38,39</sup> Because of the temperature sensitivity of *P. chlororaphis* combined with the need for methods of storage and transport that do not require a cold chain or temperature control, we next evaluated the efficacy of diverse MPN coatings to protect these microbes from high temperatures and humidity.

At 4 °C, the temperature of refrigerated cold-chain transport, even uncoated bacteria survive (Figure S5). However, the advantage of MPNs lies in their ability to protect microbes at temperatures at which uncoated cells do not survive. In our previous work, we had observed that the composition of the MPN coating alters the efficacy of protection.<sup>21</sup> Yet, the specific components that would enable optimal survival against specific stressors cannot yet be determined a priori. We therefore screened different MPN compositions composed of metal ions and polyphenols for P. chlororaphis stability. As can be seen in Figure 2a, at low temperatures, there is no statistical significance between the survival of microbes coated with the different MPNs. However, at the transition temperature of 35 °C, no uncoated cells survive, while some of the coated microbes do. This difference is statistically significant (p<0.005) and demonstrates the large difference in survival afforded by optimized MPNs. The marked survivability of P. chlororaphis at 35 °C with only certain MPNs further confirms that the MPN composition remains an essential factor in protection.

The lack of a difference in the protective efficiency of MPNs across metal ions evaluated with TA motivated further screening of polyphenols (Figure 2d). In prior work, the rigidity and thickness of the MPN coating has been determined for a variety of polyphenols and metal ions. Both the number of chelation sites (the number of catechols in the molecule) and the cation valency impact the thickness and morphology of coatings, ranging from somewhat rigid coatings 10 nm thick (usually found with TA and a trivalent cation) to very rigid and thin coatings only about 2 nm thick (usually observed with GA and a trivalent cation such as Fe<sup>3+</sup> and Mn<sup>3+</sup>. Thus, we expected the physical properties of the MPNs to differ more significantly upon variation of the polyphenol.

As expected, much larger differences in protective efficacy were observed upon variation of the polyphenol as compared to the metal (Figure 2d). In fact, these results highlight the critical importance of evaluating each of the three variables tested: metal ion used in the MPN, polyphenol used in the MPN, and the number of coating layers used. As is evidenced from the two-coating data for EGCG and Mn, this coating offers significantly more effective protection than the other coatings, with statistical significance of p < 0.05 for the other coatings. In contrast, this same coating yielded no viable cells if it was applied four times to cells (Figure 2d, right). We attribute this to the rigidity of this coating, which provided protection at two layers but inhibited growth to the point where no cells grew with four coatings. While these experiments demonstrated that some MPN combinations provided little to no protection of cells, the ability of some MPNs to protect against the initial exposure challenges demonstrated the need for further investigation.

Following the initial MPN testing, a screen of postlyophilization storage conditions was performed. The variables selected for screening are based on the harsh conditions to which these microbes could be exposed during transport and



**Figure 3.** Impact of MPN-coated *P. chlororaphis* on seed germination. (a) Images of seeds treated either with MPN-coated, lyophilized *P. chlororaphis* (green box) or with water only (red box). (b) Percentages of seed germination after applying water-only, fresh live, lyophilized,  $Mn^{II}$ -EGCG-coated lyophilized *P. chlororaphis* in agar plates for five days. Error bars represent standard deviations of *n* = 3 replicates. Percentages of (c) bok choy seed and (d) soy bean germination after applying water-only, fresh live cells only, fresh live cells with  $Mn^{II}$ , fresh live cells with EGCG, lyophilized cells only, lyophilized cells with  $Mn^{II}$ , lyophilized cells with EGCG and  $Mn^{II}$ -EGCG-coated lyophilized *P. chlororaphis* in agar plate for five or ten days. The lyophilized cells (both coated and uncoated) were stored at 50°C and 48% RH for five days before incubation with seeds.

storage to farms where they would be distributed. Critically, many of these farms are not accessible by paved roads and do not have temperature-controlled storage for their seeds and fertilizers, so necessitating cold storage would be a non-starter. Thus, we focused on temperature and humidity preservation to ensure that the microbes survive under conditions under which they could be stored in farmland in South America and South Asia. As we previously identified differences in MPN efficacy based on the polyphenol and metal ions used for assembly on these microbes, we anticipated the observation of similar trends here in the more expansive study. Variables for stress testing of the cells included high temperatures and humidity for incubation times on the order of production and transport times to potentially challenging agricultural locations. We therefore evaluated incubation times ranging from 48 hours to 10 days. The upper temperature limit for the experiment was set at the estimated temperature a storage shed in Brazil would

reach during a warm day in the planting season, where outdoor temperatures reach 43  $^\circ C$  and 70–80% humidity.

Because of the differences in recovery observed with two and four coatings in our initial experiments (Figure 2d), for our larger evaluation of stressors, we evaluated only two coatings. As seen from CFU data (Figure 2e), MPNs are capable of protecting *P. chlororaphis* under the harshest transport and storage conditions, even enabling growth following multiple days at the highest temperature and humidity (50 °C, 48% RH for ten days, Figure 2e). Importantly, the uncoated microbes demonstrated little to no survival under similar conditions (Figure 2e). In fact, it is critical to emphasize that the uncoated microbes did survive some conditions at 37 °C storage, but in every case, 1–2 orders of magnitude fewer uncoated cells survived as compared to the coated cells. Additionally, the uncoated cells fared significantly worse under humid conditions. At 37 °C storage with humidity, no uncoated cells survived. Similarly, beyond 48 h of exposure to 50 °C, no uncoated cells survived, while many combinations of MPNs effectively protected cells. Finally, we observed significantly improved survival of coated microbes at elevated temperatures (30 °C) for extended lengths of time (two months) due to MPN coatings (Figure S4). These results emphasize the importance of MPNs for microbial protection.

Interestingly, for the majority of the stressor studies, no specific MPN significantly outperforms the rest. Based on the optimal coatings, which are GA and Fe, GA and Mn, and EGCG and Mn, we anticipate that protection against heat and humidity is dependent on the rigidity of the coatings, as the thinner, more rigid coatings formed from GA and EGCG were favored for protection in these cases.

#### Impact of Microbes on Seed Germination

Though the protection of microbes is important, we additionally sought to investigate whether the impressive recovery results would translate to seed germination rates, the ultimate goal of P. chlororaphis use. We applied fresh live, lyophilized and MPN-coated, or just lyophilized P. chlororaphis to a variety of seeds, including corn, bok choy, sprouts, two types of radishes, and dill (Figure 3b). The MPN employed for seed germination studies was the one found to be optimal in the initial studies (Figure 2d) and continued to be one of the best coatings across the expanded stressor experiments (Figure 2e), which was EGCG and Mn. Initial studies on a variety of seeds were important to establish whether any observed germination effects were seed-dependent. As can be seen, MPN-coated cells, despite their harsh storage conditions at 50°C and 48% RH, yielded higher rates of germination than any other condition, including seeds treated with the fresh cells. Within each type of seed, statistically significant differences were observed between the conditions (P < 0.05). These initial studies provided support for our hypothesis that seeds growing in nutrient-depleted environments would benefit from the presence of nitrogen-fixing bacteria, such as P. chlororaphis. However, these initial studies did not enable clarification of why the MPN-coated cells were superior even than to fresh cells.

This lack of clarity as to whether improvements were due to the cells themselves, the components of the MPNs, or a combination of the two led to further investigation of the germination rate that incorporated additional controls. To further investigate the observed improvement, we studied germination with bok choy and sprout seeds because they are relatively rapid germinators (Figure 3c,d). For bok choy, after five days, the fresh cells improved germination over the wateronly cells by 16.7%, while the lyophilized bacteria exhibited slightly smaller improvements (13.7%). Importantly, MPNcoated cells improved germination by 58.3%, significantly more than under any other conditions, including fresh cells with the individual MPN components added (Figures 3c, S7).

After ten days, overall germination increased, but the relative percentages of germinated cells remained consistent. Similar results were observed with sprout seeds. After five days, the fresh cells had 8.3% improved germination over water-only, while applying lyophilized cells had slightly lower germination than the water alone, although this difference is not statistically significant (2.1% less) (Figure 3d, S7). In contrast, MPN-coated cells had 47.9% higher germination than that of water only. Additionally, combining freeze-dried uncoated *P. chlororaphis* with alginate beads (500 nm diameter) coated in

the MPN did not show statistically significant differences relative to the seeds treated with only freeze-dried cells (Figure S8). These improvements confirm that it is the combination of the MPN coatings with the microbes that leads to improvements, even when the microbes are stored under exceptionally harsh conditions. The results further demonstrate the immense power of MPNs to maintain microbial viability and directly translate that to improved seed germination.

#### CONCLUSIONS

Taken together, these results demonstrate the power of some MPN assemblies to protect temperature-sensitive microbes from high temperatures and humidity. Critically, the microbes evaluated are capable of fixing nitrogen in soil and could be used in regenerative agriculture applications. As expected, MPNs protected P. chlororaphis from lyophilization, as we have shown with other strains previously. Importantly, though, upon screening combinations of polyphenols and metal ions, we found MPN combinations that protect microbes from exceptional heat and humidity. Importantly, these are not necessarily the types of MPNs that we have previously identified as optimal, as they are assembled with smaller polyphenols that form thinner, more compact shells on microbes that seem to be more rigid than some of the larger polyphenols that we have tested. Following the optimization of the coatings, we demonstrate long-term protection. Our ability to protect P. chlororaphis for 10 days at extremely high temperatures (50 °C) and humidity as well as slightly lower temperatures (30 °C) for months pushes the protective ability of our coatings into the realm of utility for regenerative agriculture by negating the need for either microbial growth in bioreactors on-site or employing cold chain transport to enable the microbes to reach their destination. Further, we demonstrated that the microbes protected by MPN coatings yielded significantly higher germination rates for multiple types of seeds and, more specifically, bok choy and sprouts, as compared to seeds treated with fresh microbes. These results are promising for the application of these microbes as replacements for chemical fertilizers at scale. Long-term, we anticipate these coatings will enable the storage and transport of critical microbial species without cold chain transport and enable microbes to be viable, sustainable alternatives to chemically-produced fertilizer.

#### METHODS

#### **Encapsulation of Bacteria with MPNs**

*P. chlororaphis* were coated in MPNs as previously published.<sup>1</sup> Briefly, 125  $\mu$ L of aqueous solution of phenol (TA-1.6 mg mL<sup>-1</sup>; GA-1.5 mg mL<sup>-1</sup>; EGCG-2.7 mg mL<sup>-1</sup>, 50% from tea extract) and 125  $\mu$ L of aqueous solution of the cation to be used (iron chloride (0.24 mg mL<sup>-1</sup>), zinc sulfate heptahydrate (0.42 mg mL<sup>-1</sup>), aluminum chloride (0.19 mg mL<sup>-1</sup>), or manganese sulfate monohydrate (0.72 mg ml<sup>-1</sup>)) were added sequentially to an aqueous suspension of cells (250  $\mu$ L, OD<sub>600</sub> of 3.0). The resulting suspension was mixed vigorously for 10 s. A volume of 0.5 mL of MOPS buffer (20 mM, pH 7.4) was then added to form a stable MPN shell. The resulting encapsulated cells were washed with ultrapure water three times to remove any residual starting materials. The coating process can be repeated as many times as desired; here, we either used two total coatings or four total coatings. Seed germination studies were performed in 0.5% agar plates made with ultrapure water. Seeds were inserted in the agar to halfway down the seed, and 10  $\mu$ L of the relevant microbial sample was added to each seed. Samples were either ultrapure water or microbes and MPN components in ultrapure water. For samples containing cells,  $1 \times 10^7$  bacteria per seed were added. To add seeds, *P. chlororaphis* was diluted to concentrations of  $1 \times 10^9$  bacteria/mL in ultrapure water. Seeds were allowed to incubate for five days with the Petri dish cover on at ambient temperature under grow lights. Germinated seeds were then counted. For ten-day studies, the lids of the dishes were removed for the second half of the incubation time (the final five days). Following ten days of incubation, the germinated seeds were counted.

### ASSOCIATED CONTENT

#### Data Availability Statement

All data are available in the main text or the Supporting Information.

#### **Supporting Information**

The Supporting Information is available free of charge at https://pubs.acs.org/doi/10.1021/jacsau.3c00426.

Additional methods and results (Figures S1–S8) (PDF)

### AUTHOR INFORMATION

#### **Corresponding Author**

Ariel L. Furst – Department of Chemical Engineering and Center for Environmental Health Sciences, Massachusetts Institute of Technology, Cambridge, Massachusetts 02139, United States; orcid.org/0000-0001-9583-9703; Email: afurst@mit.edu

#### **Authors**

Benjamin Burke – Department of Chemical Engineering, Massachusetts Institute of Technology, Cambridge, Massachusetts 02139, United States

Gang Fan – Department of Chemical Engineering, Massachusetts Institute of Technology, Cambridge, Massachusetts 02139, United States; © orcid.org/0000-0002-4185-5692

Pris Wasuwanich – Department of Chemical Engineering, Massachusetts Institute of Technology, Cambridge, Massachusetts 02139, United States; © orcid.org/0000-0003-4590-3863

Evan B. Moore – Department of Chemical Engineering, Massachusetts Institute of Technology, Cambridge, Massachusetts 02139, United States

Complete contact information is available at: https://pubs.acs.org/10.1021/jacsau.3c00426

#### **Author Contributions**

<sup>†</sup>B.B and G.F. contributed equally

#### Notes

The authors declare the following competing financial interest(s): A patent on MPNs has been filed through MIT by A.L.F.

Safety Considerations: No unexpected or unusually high safety hazards were encountered.

### ACKNOWLEDGMENTS

This work was supported by the Army Research Office (W911NF-22-1-0106), the National Institutes of Health-New Innovator Award (1DP2GM154015), the National Institutes of Health-NIEHS Core Center Grant (P42-ES027707), the National Institutes of Health-NIEHS Core Center Grant (P30-ES002109), the CIFAR Azrieli Global Scholars Program, the MIT J-WAFS Program, the MIT Climate and Sustainability Consortium, and the MIT Deshpande Center.

#### REFERENCES

(1) Molina-Santiago, C.; Matilla, M. A. Chemical Fertilization: A Short-Term Solution for Plant Productivity? *Microb Biotechnol* **2020**, *13* (5), 1311–1313.

(2) Tilman, D.; Balzer, C.; Hill, J.; Befort, B. L. Global Food Demand and the Sustainable Intensification of Agriculture. *Proceedings of the National Academy of Sciences* **2011**, *108* (50), 20260–20264.

(3) Rosa, L.; Gabrielli, P. Energy and Food Security Implications of Transitioning Synthetic Nitrogen Fertilizers to Net-Zero Emissions. *Environmental Research Letters* **2023**, *18* (1), 014008.

(4) Kopittke, P. M.; Menzies, N. W.; Wang, P.; McKenna, B. A.; Lombi, E. Soil and the Intensification of Agriculture for Global Food Security. *Environ Int* **2019**, *132*, No. 105078.

(5) Kyriakou, V.; Garagounis, I.; Vourros, A.; Vasileiou, E.; Stoukides, M. An Electrochemical Haber-Bosch Process. *Joule* 2020, *4* (1), 142–158.

(6) EPA. Inventory of U.S. Greenhouse Gas Emissions and Sinks: 1990-2020. U.S. Environmental Protection Agency, 2020; EPA 430-R-22-003.

(7) Dirzo, R.; Raven, P. H. Global State of Biodiversity and Loss. *Annu Rev Environ Resour* **2003**, 28 (1), 137–167.

(8) Vitousek, P. M.; Aber, J. D.; Howarth, R. W.; Likens, G. E.; Matson, P. A.; Schindler, D. W.; Schlesinger, W. H.; Tilman, D. G. Human Alteration of the Global Nitrogen Cycle: Sources and Consequences. *Ecological applications* **1997**, *7* (3), 737–750.

(9) Cheng, Y.; Wang, J.; Zhang, J.-B.; Müller, C.; Wang, S.-Q. Mechanistic Insights into the Effects of N Fertilizer Application on N 2 O-Emission Pathways in Acidic Soil of a Tea Plantation. *Plant Soil* **2015**, 389, 45–57.

(10) Owuor, P. O.; Othieno, C. O.; Kamau, D. M.; Wanyoko, J. K. Effects of Long-Term Fertilizer Use on a High-Yielding Tea Clone AHPS15/10: Soil PH, Mature Leaf Nitrogen, Mature Leaf and Soil Phosphorus and Potassium. *International Journal of Tea Science (IJTS)* **2011**, 8 (1), 15–51.

(11) Schnitkey, G.; Zulauf, C.; Swanson, J.; Paulson, N. 2022 Planting Decisions, Nitrogen Fertilizer Prices, and Corn and Soybean Prices *farmdoc daily*; Department of Agricultural and Consumer Economics, University of Illinois at Urbana-Champaign, 2021, *11*, 145.

(12) Komarek, A. M.; Drogue, S.; Chenoune, R.; Hawkins, J.; Msangi, S.; Belhouchette, H.; Flichman, G. Agricultural Household Effects of Fertilizer Price Changes for Smallholder Farmers in Central Malawi. *Agric Syst* **2017**, *154*, 168–178.

(13) Brownlie, W. J.; Sutton, M. A.; Cordell, D.; Reay, D. S.; Heal, K. V; Withers, P. J. A.; Vanderbeck, I.; Spears, B. M. Phosphorus Price Spikes: A Wake-up Call for Phosphorus Resilience. *Front Sustain Food Syst* **2023**, *7*, 1088776.

(14) O'Toole, P. W.; Marchesi, J. R.; Hill, C. Next-Generation Probiotics: The Spectrum from Probiotics to Live Biotherapeutics. *Nature Microbiology*. **2017**, 1–6.

(15) El Hage, R.; Hernandez-Sanabria, E.; Van de Wiele, T. Emerging Trends in "Smart Probiotics": Functional Consideration for the Development of Novel Health and Industrial Applications. *Frontiers in Microbiology.* **2017**, 1889.

(16) Olle, B. Medicines from Microbiota. *Nat Biotechnol* **2013**, *31* (4), 309–315.

(17) Verbon, E.; Liberman, L. M. Beneficial Microbes Affect Endogenous Mechanisms Controlling Root Development | Elsevier Enhanced Reader. *Trends Plant Sci* **2016**, *21* (3), 218–229.

(18) Mendes, R.; Garbeva, P.; Raaijmakers, J. M. The Rhizosphere Microbiome: Significance of Plant Beneficial, Plant Pathogenic, and Human Pathogenic Microorganisms. *FEMS Microbiol Rev* **2013**, *37* (5), 634–663.

(19) Walker, T. W. N.; Kaiser, C.; Strasser, F.; Herbold, C. W.; Leblans, N. I. W.; Woebken, D.; Janssens, I. A.; Sigurdsson, B. D.; Richter, A. Microbial Temperature Sensitivity and Biomass Change Explain Soil Carbon Loss with Warming. *Nature Climate Change 2018 8:10* **2018**, *8* (10), 885–889.

(20) Compant, S.; Samad, A.; Faist, H.; Sessitsch, A. A Review on the Plant Microbiome: Ecology, Functions, and Emerging Trends in Microbial Application. *J Adv Res* **2019**, *19*, 29–37.

(21) Wasuwanich, P.; Fan, G.; Burke, B.; Furst, A. L. Metal-Phenolic Networks as Tuneable Spore Coat Mimetics. *J Mater Chem B* **2022**, *10*, 7600–7606.

(22) Fan, G.; Wasuwanich, P.; Rodriguez-Otero, M. R.; Furst, A. L. Protection of Anaerobic Microbes from Processing Stressors Using Metal–Phenolic Networks. *J Am Chem Soc* 2022, 144 (6), 2438–2443.

(23) Fan, G.; Cottet, J.; Rodriguez-Otero, M. R.; Wasuwanich, P.; Furst, A. L. Metal–Phenolic Networks as Versatile Coating Materials for Biomedical Applications. *ACS Appl Bio Mater* **2022**, *5*, 4687– 4695.

(24) Liu, P.; Shi, X.; Zhong, S.; Peng, Y.; Qi, Y.; Ding, J.; Zhou, W. Metal-Phenolic Networks for Cancer Theranostics. *Biomater Sci* **2021**, 9 (8), 2825–2849.

(25) Chen, J.; Pan, S.; Zhou, J.; Zhong, Q. Z.; Qu, Y.; Richardson, J. J.; Caruso, F. Programmable Permeability of Metal-Phenolic Network Microcapsules. *Chemistry of Materials* **2020**, *32*, 6975.

(26) Rahim, Md. A.; Kristufek, S. L.; Pan, S.; Richardson, J. J.; Caruso, F. Phenolic Building Blocks for the Assembly of Functional Materials. *Angewandte Chemie International Edition* **2019**, *58* (7), 1904–1927.

(27) Guo, Z.; Xie, W.; Lu, J.; Guo, X.; Xu, J.; Xu, W.; Chi, Y.; Takuya, N.; Wu, H.; Zhao, L. Tannic Acid-Based Metal Phenolic Networks for Bio-Applications: A Review. *J Mater Chem B* **2021**, 9 (20), 4098–4110.

(28) Johansson, J. F.; Paul, L. R.; Finlay, R. D. Microbial Interactions in the Mycorrhizosphere and Their Significance for Sustainable Agriculture. *FEMS Microbiol Ecol* **2004**, *48* (1), 1–13.

(29) Raio, A.; Puopolo, G. Pseudomonas Chlororaphis Metabolites as Biocontrol Promoters of Plant Health and Improved Crop Yield. *World J Microbiol Biotechnol* **2021**, 37 (6), No. 99.

(30) Kanchiswamy, C. N.; Malnoy, M.; Maffei, M. E. Bioprospecting Bacterial and Fungal Volatiles for Sustainable Agriculture. *Trends Plant Sci* **2015**, *20* (4), 206–211.

(31) Chen, Y.; Shen, X.; Peng, H.; Hu, H.; Wang, W.; Zhang, X. Comparative Genomic Analysis and Phenazine Production of Pseudomonas Chlororaphis, a Plant Growth-Promoting Rhizobacterium. *Genom Data* **2015**, *4*, 33–42.

(32) Craig, K.; Johnson, B. R.; Grunden, A. Leveraging Pseudomonas Stress Response Mechanisms for Industrial Applications. *Front Microbiol* **2021**, *12*, No. 660134.

(33) Brilli, F.; Pollastri, S.; Raio, A.; Baraldi, R.; Neri, L.; Bartolini, P.; Podda, A.; Loreto, F.; Maserti, B. E.; Balestrini, R. Root Colonization by Pseudomonas Chlororaphis Primes Tomato (Lycopersicum Esculentum) Plants for Enhanced Tolerance to Water Stress. *J Plant Physiol* **2019**, *232*, 82–93.

(34) Palmfeldt, J.; Rådström, P.; Hahn-Hägerdal, B. Optimisation of Initial Cell Concentration Enhances Freeze-Drying Tolerance of Pseudomonas Chlororaphis. *Cryobiology* **2003**, 47 (1), 21–29.

(35) Yun, G.; Richardson, J. J.; Biviano, M.; Caruso, F. Tuning the Mechanical Behavior of Metal-Phenolic Networks through Building Block Composition. *ACS Appl Mater Interfaces* **2019**, *11* (6), 6404–6410.

(36) Guo, J.; Richardson, J. J.; Besford, Q. A.; Christofferson, A. J.; Dai, Y.; Ong, C. W.; Tardy, B. L.; Liang, K.; Choi, G. H.; Cui, J.; Yoo, P. J.; Yarovsky, I.; Caruso, F. Influence of Ionic Strength on the Deposition of Metal-Phenolic Networks. *Langmuir* **2017**, 33 (40), 10616–10622.

(37) Guo, J.; Ping, Y.; Ejima, H.; Alt, K.; Meissner, M.; Richardson, J. J.; Yan, Y.; Peter, K.; von Elverfeldt, D.; Hagemeyer, C. E.; Caruso, F. Engineering Multifunctional Capsules through the Assembly of Metal-Phenolic Networks. *Angewandte Chemie International Edition* **2014**, 53 (22), 5546–5551.

(38) Chen, Q.; Qian, J.; Yang, H.; Wu, W. Sustainable Food Cold Chain Logistics: From Microenvironmental Monitoring to Global Impact. *Compr Rev Food Sci Food Saf* **2022**, *21* (5), 4189–4209.

(39) Han, J.-W.; Zuo, M.; Zhu, W.-Y.; Zuo, J.-H.; Lü, E.-L.; Yang, X.-T. A Comprehensive Review of Cold Chain Logistics for Fresh Agricultural Products: Current Status, Challenges, and Future Trends. *Trends Food Sci Technol* **2021**, *109*, 536–551.

#### NOTE ADDED AFTER ASAP PUBLICATION

This paper was published ASAP on October 30, 2023, with an error in Figure 3a. The corrected version was reposted November 9, 2023.